

TECHTHANE[®] ES-125 TDI POLYESTER PREPOLYMER**DESCRIPTION**

TECHTHANE ES-125 is an advanced, high performance polycaprolactone polyester TDI prepolymer, which, when reacted with 4,4-Methylene-bis-[ortho-chloroaniline] (MBCA), yield elastomers of approximately 60 Shore A hardness. Notable characteristics are its combination of low hardness, high physical properties, high abrasion resistance, high resistance to oils and solvents, high hydrolysis resistance for a polyester, and long pot life. Typical applications include mining screens, rolls, linings, belt cleaners, and seals.

PROPERTIES OF LIQUID PREPOLYMER

PROPERTY	VALUE
Liquid-Solid Transition Point, °F (°C)	110 (43)
Available Isocyanate Content	3.30-3.60
Viscosity Brookfield, cps @ 212°F (100°C)	700
Specific Gravity @ 75°F (24°C)	1.16
Specific Gravity @ 212°F (100°C)	1.12

PROPERTIES OF CURED ELASTOMER

PROPERTY	VALUE
Hardness, Shore A/D (ASTM D2240)	60 A
Tensile Strength, psi (ASTM D412)	3500
Elongation, % (ASTM D412)	540
100% Modulus, psi (ASTM D412)	290
300% Modulus, psi (ASTM D412)	520
Tear Strength, Die-C, pli (ASTM D624)	195
Tear Strength, Split, pli (ASTM D470)	26
Rebound, Bashore, % (ASTM D2632)	31
Compression Set, 22 hrs. @ 158°F, %, Method B	7
Specific Gravity (ASTM D792)	1.15
Bell Brittle Point, °F (°C) (ASTM D746)	<-80 (-65)

PROCESSING SUMMARY

PROPERTY	VALUE
MBCA level, pph, approximate	10.10
Prepolymer temperature, °F (°C)	212 (100)
Mold temperature, °F (°C)	240 (115)
Pot Life @ 212°F (100°C), minutes	12
Cure @ 240°F (110°C), hours	1-2
Post Cure @ 212°F (100°C), hours	16

INFORMATION BASED ON 92% THEORY

PROCESSING

Thawing

TECHTHANE prepolymers will solidify at temperatures below their liquid/solid transition point, which for ES-125 is high at 110°F (43°C). If solidified, pre-thawing can normally be achieved by heating the container to a maximum of 180°F (80°C) using a melting oven, thermostatically-controlled blanket heater, or other uniform heating device (heat bands are not recommended) for a period of 12--24 hours. Re-blend contents thoroughly after each thawing.

Re-blending

Prepolymers must be re-blended thoroughly prior to use to ensure homogeneity of the prepolymer. This is especially important if the prepolymer has solidified or possibly solidified, or if less than the entire quantity in the container is to be used at one time. Re-blend prior to each use for best results.

Degassing

Removal of any air which has become entrained in the prepolymer can normally be achieved either by heating the prepolymer to 180-200°F (80-93°C) for 15-20 minutes, or preferably via vacuum and agitation. Either method is complete when the majority of air is removed.

Casting

To ensure optimum physical properties and surface finish, molds should be heated to or slightly higher than cure temperature. Application of mold release agents should be in accordance with release agent manufacturer's guidelines. Mold release can be avoided by having molds Teflon® coated.

Curing

Suggested: Cure for 2 hours at 240°F (115°C), remove from mold if desired, post-cure for 16 hours at 212°F (100°C)

Note: If using curatives other than MBCA such as Ethacure® 300 or Techcure™ 915B, refer to curative manufacturer's suggested cure cycles.

AVAILABILITY

TECHTHANE prepolymers are packaged in 44 lb. (20 kg) pails and 451 lb. (205 kg) drums. Specific quantities and special packaging are available by request.

STORAGE AND SHELF LIFE

TECHTHANE prepolymers are packaged sealed under an argon gas blanket. Containers should be kept in this condition and stored in a cool, dry area that is protected from direct sunlight until they are to be used. A container that has been opened should be resealed immediately, and if its contents are not to be used within 24 hours, it must be purged with argon or clean dry nitrogen to prevent moisture contamination.

In the absence of heat and moisture, TECHTHANE prepolymers are stable and have a shelf life of a minimum of 1 year. In the presence of heat, however, the NCO of all prepolymers decreases, affecting their reactivity. The following is a summary of the maximum recommended time that prepolymers should be maintained at the given temperature without significant decrease in NCO:

TEMPERATURE	MAXIMUM STORAGE TIME
90°F (32°C)	6 weeks
180°F (82°C)	36 hours
200°F (93°C)	12 hours
212°F (100°C)	8 hours

SAFETY

TECHTHANE prepolymers, in their uncured liquid form, contain a small amount of free toluene-diisocyanate (TDI) which can cause severe irritation to the eyes, skin, respiratory system, and mucous membranes. Contact by inhalation, skin, eye, or ingestion must be avoided. All guidelines for handling TDI-containing materials must be followed when using TECHTHANE prepolymers.

To avoid inhalation, forced air ventilation must be used for all indoor applications. When working in tanks and other confined areas, or anywhere the TLV is exceeded, fresh air breathing equipment must be worn. Chemical cartridge masks suitable for organic vapors and approved by MSHA/OSHA may be used under some conditions with adequate ventilation. To avoid contact with skin or clothing, protective clothing must be worn at all times.

Refer to the Material Safety Data Sheet (MSDS) for further information prior to use of this material.

These products are intended for use by professional casting facilities only.

FOR INDUSTRIAL USE ONLY

Ethacure® is a registered trademark of Albamarle Corporation
Teflon® is a registered trademark of Dupont Corporation

17 Aug. 2001

The information herein is to assist persons in determining whether our products are suitable for their applications. Because we cannot anticipate the conditions under which this information or our products may be used, the information should not be construed as an express or implied warranty of merchantability or fitness for any particular purpose. Users are advised to conduct their own tests to determine the suitability of any of our products for any particular purpose. The exclusive remedy for all proven claims is replacement of our products and in no event shall we be liable for special, incidental, or consequential damages. Nothing in this bulletin is to be considered as a recommendation to use this product so as to infringe on any patent.